

## Technical Data Sheet ISSUED JANUARY 2026

### **PRODUCT DESCRIPTION**

WPA Rapid is a waterborne, flexible waterproofing membrane, utilising next generation, self-crosslinking technology, which enables the membrane to achieve cured properties rapidly. WPA Rapid is designed for use under tiles in internal and exterior applications.

Recommended for:

- Bathrooms
- Laundries
- Balconies
- Podium Decks
- Terraces
- Roof tops
- Waterproofing of areas subsequently covered by ceramic or stone tiles

### **FEATURES AND BENEFITS**

- Class III in accordance with AS/NZS 4858 and AS 4654.1
- Heavy duty applications
- Fast curing
- Low VOC
- Compatible with a wide range of tile adhesives
- Permanently flexible
- Completely resistant to re-emulsification (when fully cured)
- Excellent adhesion to a wide variety of substrates

### **APPLICATION PROCEDURE**

#### **Substrates**

WPA Rapid is suitable for concrete, render, screeds, block work, fibre-cement sheeting, wet area grade plasterboard, lightweight structural flooring and PAA certified structural grade marine plywood.

Always contact the manufacturer if in any doubt about the suitability of the substrate.

#### **Preparation**

All surfaces to be waterproofed must be firm, clean, dry, sound and smooth. All laitance, grease, oil, wax, curing compounds, loose material, paint and any other contaminants which may reduce or prevent adhesion must be mechanically removed. Masonry surfaces must be pointed flush and surface defects repaired.

New concrete must be cured for a minimum of 28 days.

Render and cement screeds must be cured for a minimum of 7 days.

Fibre cement sheeting, water resistant plasterboard, lightweight structural flooring and plywood must be installed in accordance with the manufacturers' installation requirements.



WPA Rapid requires a fillet (bond breaker) using WPA MS, WPA SPUR sealant at all horizontal and vertical transitions. For optimal performance, incorporate WPA Elastoband SG or WPA Butyl Tape at all transitions.

#### **Static Crack Treatment**

For cracks less than 1mm, clean cracks thoroughly before filling with WPA MS, WPA SPUR.

WPA Rapid cannot span gaps. For dynamic cracks/expansion joints and control joints, the use of WPA Elastoband SG or WPA Butyl Tape systems is recommended. Contact the WPA Technical Department for further advice.

#### **Priming**

Dry porous substrates can be primed with WPA 360, WPA SB or WPA 460 primers.

Damp substrates with a RH of <75% must be primed with WPA 460.

Substrates with an RH >75% must be primed with WPA 560 Moisture Seal.

Green cementitious screed can be primed with WPA 260.

Non-Porous substrates such as metals or PVC must be primed with WPA 160.

Lightweight structural flooring must be primed with WPA 460.

Apply the primer to the prepared substrate by using a brush or roller in accordance with the relevant product's Technical Data Sheet. Allow the primer to fully dry prior to commencing the application of WPA Rapid.

#### **Application**

WPA Rapid must be applied in accordance with the applicable provisions of the National Construction Code.

Prior to application, stir the contents thoroughly. Using a brush or roller, apply the first coat of WPA Rapid after the primer has fully dried. Apply an even and consistent coat of approximately 750 microns wet film thickness.

Once the first coat has dried, apply a second coat of WPA Rapid at right angles to the first coat. Apply an even and consistent coat of approximately 750 microns wet film thickness.

WPA Rapid must be applied with a minimum of two coats to achieve a dry film thickness of not less than 1.0mm (1000 microns). Test the depth of coats with a wet film thickness gauge at regular intervals during installation.

## Technical Data Sheet ISSUED JANUARY 2026

### Performance Data and Physical Properties @23°C & 55% RH

- Allow a minimum 4 hours between coats.
  - Allow 24 hours after the final coat before tiling.
  - WPA Rapid will dry to a solid grey colour when fully cured. This will indicate the membrane is fully cured ready for flood testing.
  - Allow longer times in cool or damp weather conditions.
- (NOTE: At temperatures lower than 23°C the curing time will be significantly reduced).

### Wet Form

- Appearance .....Grey
- Dry solid content ..... > 60%
- VOC ..... 0.08grams/litre

### Cured Membrane

- Elongation.....>300%
- Water vapour transmission.....0.30g/M<sup>2</sup>/24hrs

### Limitations

Do not apply **WPA Rapid**:

- Over damp, wet or contaminated substrates.
- If it is raining or if rain is imminent.
- Directly over any existing coatings.
- Directly to particle board flooring (Ceramic tile underlay must be installed).
- As an exposed membrane.
- As a wear surface for foot or vehicle traffic.
- Where ambient or surface temperatures are below 10°C or greater than 35°C.
- To areas subject to negative hydrostatic pressure or rising damp.
- To areas of continuous immersion such as swimming pools, ponds, water features or water tanks.

To reduce the possibility of surface contamination, it is recommended that tiling be carried out as soon as the membrane has cured.

### Clean Up

Clean tools and equipment with warm water and detergent while the membrane is still wet. Cured WPA Rapid can only be removed by mechanical means.

### Packaging

15 litre plastic pails.

### Coverage

Approx. 1.5 litres per M<sup>2</sup> at 1mm dry film thickness (10M<sup>2</sup> per drum).

The coverage figures are theoretical due to wastage. Depending on the porosity and profile of the substrate, coverage figures may be reduced.

### Shelf Life

12 months if stored in unopened sealed containers, when kept in a cool, dry storage area.

If stored at high temperatures, the shelf life may be reduced.

### SAFETY INSTRUCTIONS

For instructions on the safe use of WPA Rapid please refer to the latest version of the Safety Data Sheet available from our website [www.wpa-us.com.au](http://www.wpa-us.com.au).

### WARRANTY CONDITIONS

Bayset Pty Ltd trading as Waterproofing Products Australia (Bayset) offers a limited warranty in respect of this product, subject to certain terms and conditions set out in the warranty documentation which has been made available at [www.bayset.com.au](http://www.bayset.com.au). Please contact Bayset directly to obtain a copy of the warranty documentation relevant to this product.

### DISCLAIMER

The technical information and application advice given in this Technical Data Sheet is based on the present state of Bayset Pty Ltd's best scientific and practical knowledge and is intended to give a fair description of the product and its capabilities. As the information contained herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness, either expressed or implied, is given other than those required by law. In practice, the substrate and environmental conditions vary widely, making it essential for the user to determine the product's suitability for a particular application and that the product is not used beyond its physical limitations. The user is responsible for checking the suitability of products for their intended use.

### \*NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Waterproofing Products Australia either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Waterproofing Products Australia, are responsible for carrying out procedures appropriate to a specific application.

DOCUMENT CONTROL	
Product	WPA Rapid
Initial Issue	November 2015
Technical Amendment	January 2026
Author	SR

Technical Data Sheets are subject to change without notice. For latest revision, check our website at [www.wpa-us.com.au](http://www.wpa-us.com.au)  
This is a CONTROLLED document under WPA's Quality System.